

Sikadur® - 31 CF Normal (formerly Sikadur® 731) 2-part thixotropic epoxy adhesive

Product Description

Sikadur-31® CF Normal is a solvent-free, moisture tolerant, thixotropic, structural two part adhesive and repair mortar, based on a combination of epoxy resins and special fillers.

Uses

As a structural adhesive and mortar for :

- Concrete elements
- Hard natural stone
- Ceramics, fiber cement
- Mortar, Bricks, Masonry
- Steel, Iron, Aluminium
- Wood
- Polyester, Epoxy
- Glass

As a repair mortar and adhesive

- Corners and edges
- Holes and void filling
- Vertical and overhead use

Joint filling and crack sealing:

- Joint and crack aris / edge repair

Characteristics / Advantages

- Easy to mix and apply
- Suitable for dry and damp concrete surfaces
- Very good adhesion to most construction materials
- High strength adhesive
- Thixotropic: non-sag in vertical and overhead applications
- Solvent free
- Hardens without shrinkage
- Different coloured components (for mixing control)
- No primer needed
- High initial and ultimate mechanical strength
- Good abrasion resistance
- Impermeable to liquids and water vapour
- Good chemical resistance

Tests

Approval / Standards

Test according

- | | |
|---------------|-------------------------------------------------------|
| ASTM C881M-02 | – Type I, Grade 3, Class B+C |
| EN 1504-4 | – Adhesive for repair mortar |
| ASTM 638-08 | – Tensile strength and elongation at break of plastic |
| ASTM D 570-81 | – Water absorption of epoxy (24-hr immersion) |
| EN 13501-1 | – Fire Classification as “ Inflammable products” |
| BS 6319 | – Flexural, tensile, bond strength test |



Product Data

Form

Colour	Part A:	white
	Part B:	dark grey
	Parts A+B mixed:	concrete grey

Packaging	6 kg (A+B) Pre-batched unit
------------------	-----------------------------

Storage

Storage Conditions / Shelf-Life	24 months from date of production if stored properly in undamaged and unopened original sealed packaging in cool and dry conditions. Protect from direct sunlight and frost.
----------------------------------------	------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

Technical Data

Chemical Base	Epoxy resin.
----------------------	--------------

Density	1.90 + 0.1 kg/l (part A) (at +23°C) 1.90 + 0.1 kg/l (part B) (at +23°C) 1.90 + 0.1 kg/l (part A+B mixed) (at +23°C) (evacuated)
----------------	---------------------------------------------------------------------------------------------------------------------------------------

Sag flow	On vertical surfaces, it is non-sag up to 15 mm thickness. (EN 1799)
-----------------	----------------------------------------------------------------------

Shrinkage	Hardens without shrinkage.
------------------	----------------------------

Thermal Expansion Coefficient	59×10^{-6} per °C (Temp. range +23°C - +60°C) (according EN 1770)
--------------------------------------	----------------------------------------------------------------------------

Thermal Stability	Heat Deflection Temperature (HDT): (according to ISO 75) HDT = +49°C (7 days / +23°C) (thickness 10 mm)
--------------------------	------------------------------------------------------------------------------------------------------------

VOC Data	VOC content (ready to use) not exceeding 250 gm/litre [Type of Regulated Adhesives and Regulated Sealants under the Air Pollution Control (volatile organic compounds) Regulation of Hong Kong: (Other adhesives).
-----------------	---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

Mechanical / Physical Properties

Compressive Strength

(according to DIN EN 196)

Curing time	+10°C	+23°C	+30°C
1 day	25 - 35 N/mm ²	45 - 55 N/mm ²	50 - 60 N/mm ²
3 days	40 - 50 N/mm ²	55 - 65 N/mm ²	60 - 70 N/mm ²
7 days	50 - 60 N/mm ²	60 - 70 N/mm ²	60 - 70 N/mm ²

Flexural Strength

(according to DIN EN 196)

Curing time	+10°C	+23°C	+30°C
1 day	11 - 17 N/mm ²	20 - 30 N/mm ²	20 - 30 N/mm ²
3 days	20 - 30 N/mm ²	25 - 35 N/mm ²	25 - 35 N/mm ²
7 days	25 - 35 N/mm ²	30 - 40 N/mm ²	30 - 40 N/mm ²

Tensile Strength

(according to ISO 527)

Curing time	+10°C	+23°C	+30°C
1 day	2 - 6 N/mm ²	6 - 10 N/mm ²	9 - 15 N/mm ²
3 days	9 - 15 N/mm ²	17 - 23 N/mm ²	17 - 23 N/mm ²
7 days	14 - 20 N/mm ²	18 - 24 N/mm ²	19 - 25 N/mm ²

Bond Strength

(according to EN ISO 4624, EN 1542 and EN 12188)

Curing time	Temperature	Substrate	Bond strength
1 day	+10°C	Concrete dry	> 4 N/mm ² *
1 day	+10°C	Concrete moist	> 4 N/mm ² *
1 day	+10°C	Steel	6 - 10 N/mm ²
3 days	+10°C	Steel	10 - 14 N/mm ²
3 days	+23°C	Steel	11 - 15 N/mm ²
3 days	+30°C	Steel	13 - 17 N/mm ²

*100% concrete failure.

E-Modulus

Tensile:

Approx. 5'000N/mm²(14 days at +23°C)

(according to ISO 527)

Compressive:

Approx. 4'600 N/mm² (14 days at +23°C)

(according to ASTM D695)

Elongation at Break

0.4 ± 0.1% (7 days at +23°C)

(according to ISO 75)

Gel Time

70 minutes

(ASTM C881/C881M-02)

Consistency

0 mm

(ASTM C881/C881M-02)

Water absorption

Approx. 0.2%

(ASTM D570-81)

Strength Development

Confirm the strength development by producing cubes on site and testing them for compressive and flexural strength.

System Information

**Consumption /
Coverage**

Approx. 1.9 kg/m² per mm thick

Application Details

Substrate Quality

Mortar and concrete must be older than 28 days (dependent on environment and strength).

Verify the substrate strength (concrete, masonry, natural stone).

The substrate surface (all types) must be clean, dry and free from contaminants such as dirt, oil, grease, existing surface treatments and coatings etc.

Steel substrates must be de-rusted similar to SA 2.5.

The substrate must be sound and all loose particles must be removed.

Substrate Preparation

Concrete, mortar, stone, bricks:

Substrates must be sound, dry, clean and free from laitance, ice, standing water, grease, oils, old surface treatments or coatings and loosely adhering particles to achieve a laitance and contaminant free, open textured surface.

Steel:

Must be cleaned and prepared thoroughly to an acceptable quality i.e. by blastcleaning and vacuum. Avoid dew point conditions.

Other surfaces (polyester, epoxy, glass, ceramic):

On these substrates, pre-apply Sikafloor-156 (primer) and then, "wet on wet" apply Sikadur[®]-31 CF Normal.

Application Instructions

Mixing	Part A : Part B = 2 : 1 by weight						
Mixing Time	<p>Pre-batched units</p> <p>Mix parts A+B together for at least 3 minutes with a mixing spindle attached to a slow speed electric drill (max. 600 rpm) until the material becomes smooth in consistency and a uniform grey colour. Avoid aeration while mixing. Then, pour the whole mix into a clean container and stir again for approx. 1 more minute at low speed to keep air entrapment at a minimum. Mix only that quantity which can be used within its potlife.</p>						
Application Method / Tools	<p>When using a thin layer adhesive, apply the mixed adhesive to the prepared surface with a spatula, trowel, notched trowel, (or with hands protected by gloves).</p> <p>When applying as a repair mortar use some formwork.</p> <p>When using for bonding metal profiles onto vertical surfaces, support and press uniformly using props for at least 12 hours, depending on the thickness applied (not more than 5 mm) and the room temperature.</p> <p>Once hardened, check the adhesion by tapping with a hammer.</p>						
Layer Thickness	<p>30 mm max.</p> <p>When using multiple units, one after the other. Do not mix the following unit until the previous one has been used in order to avoid a reduction in handling time.</p>						
Potlife	<p>(200 g)</p> <table border="1"><thead><tr><th>+10°C</th><th>+23°C</th><th>+30°C</th></tr></thead><tbody><tr><td>~ 145 minutes</td><td>~ 55 minutes</td><td>~ 35 minutes</td></tr></tbody></table> <p>The potlife begins when the resin and hardener are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the potlife. To obtain longer workability at high temperatures, the mixed adhesive may be divided into portions. Another method is to chill parts A+B before mixing them (not below +5°C).</p>	+10°C	+23°C	+30°C	~ 145 minutes	~ 55 minutes	~ 35 minutes
+10°C	+23°C	+30°C					
~ 145 minutes	~ 55 minutes	~ 35 minutes					
Cleaning of Tools	Clean all tools and application equipment with Sika Colma Cleaner immediately after use. Hardener / cured material can only be mechanically removed.						
Notes on Application / Limitations	Uncured / unmixed material must be removed. Fully cured material can be disposed of as household waste under agreement with the responsible local authorities.						
Value Base	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.						

Application Conditions

Service Temperature	Sikadur-31 CF Normal must be applied at temperatures between +10°C and +30°C.
Substrate Temperature	+10°C min. / +30°C max.
Ambient Temperature	+10°C min. / +30°C max.
Relative Air Humidity	When applied to mat moisture concrete, brush the adhesive well into substrate.
Dew Point	Beware of condensation! Ambient temperature during application must be at least 3°C above dew point.

Health and Safety Information

Safety precautions	To avoid rare allergic reactions, use of protective gloves. Changes soiled work clothes and wash hands before breaks and after finishing work. When uncured, Sikadur-31 CF Normal parts A+B, are water-pollutants and must not be discharge into drains, waterways or the ground.
Ecology	Do not dispose of into water or soil but according to local regulations
Transport	Non-hazard
Toxicity	Allergic

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Sika Hongkong Ltd.
Rm. 1507-12, 15/F.,
Block A, New Trade Plaza,
6 On Ping Street, Shatin, N.T.
HONG KONG

Tel +852 2686 8108
Fax +852 2645 3671
email marketing@hk.sika.com
website www.sika.com.hk



ISO 9001 : 2008 Certificate No.: CC 446
ISO 14001 : 2004 Certificate No.: CC 2042

The product is manufactured under a HKQAA ISO 9001 / ISO 14001 certified quality / environmental management system.

Innovation & Consistency | since 1910